

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase. Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

CyberCote

waterborne flat

interior commercial

KEEP OUT OF REACH OF CHILDREN



9 418022 066576

WHITE

SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation. Harmful to aquatic life with long lasting effects.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions. Avoid release to the environment.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor or physician if you feel unwell.

IF ON SKIN (or hair): Rinse skin with plenty of soap and water. If skin irritation or rash occurs get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing. If eye irritation persists get medical advice or attention.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing.

When seeking medical advice take this container with you. Further information can be obtained from
AUST: POISONS INFORMATION CENTRE 131 126
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)
or call Resene 0800 737 363.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D323.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Dispose of rinse water onto grassy/unsalted area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

Resene CyberCote is designed to produce a tough interior flat finish on broadwall and ceiling areas (excludes wet areas).

Preparation

- Ensure surfaces to be painted are in sound condition, thoroughly sanded to a smooth finish, dry, free from dirt, dust and loose material.
- If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80).

- Oil, grease, fly spots and nicotine stains should be removed using either Resene Emulsifiable Solvent Cleaner (see Data Sheet D804) or Resene Interior Paintwork Cleaner. Rinse clean with water.

- Where staining is present the source must be removed. Nicotine and smoke staining can be sealed by application of a coat of Resene StainLock (see Data Sheet D408).

- Fill cracks and holes with a compatible filler before sealing.
- Plasterboard must be prepared to an appropriate level of finish.

Either Resene Broadwall Surface Prep & Seal (see Data Sheet D807) or Resene Broadwall 3 in 1 (see Data Sheet D810) is recommended in critical lighting areas.

- **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**

- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop for advice.

Priming

- Plasterboard and stoppings should be sealed (e.g. Resene Broadwall Waterborne Wallboard Sealer - see Data Sheet D403). Stopped fibrous plaster and oil tempered hardboards must be sealed with Resene Sureseal (see Data Sheet D42).

- Some 'soft' plasterboard preparatory products and undercoated gypsum based stoppings may not be suitable basecoats for painting under stressed conditions. Reinforcement with a saturation coat of a fully penetrating primer (such as Resene Sureseal) may be required.

- Use Resene Sureseal or Resene StainLock if the surface is water stained or has yellowed due to prolonged exposure to sunlight.

- All surfaces (except timber) which are highly absorbent, in poor condition, affected by efflorescence, friable, powdery or chalky must be primed with Resene Sureseal.

- Repaints - spot prime all bare areas with the recommended sealer/primer shown for new work and proceed as for new work.
- Stop all nailholes and cracked timber after priming.

- Resene Quick Dry (see Data Sheet D45) is the recommended primer over customwood, particle board and timber.

Application

- Using an airless spray unit with a minimum flow rate of 2 litres per minute, a FFLP 516 and fitted with a 60 mesh filter. Apply to achieve a wet film thickness of 102-127 microns with an overlap of 70%. An additional spray coat may be required depending upon colour to be applied and base coat colour. Back roll using a Resene No.1 or microfibre hybrid roller sleeve.

- Maintain good ventilation throughout the drying and post application curing period to ensure the paint is properly cured. This may require use of an extraction system when painting in marginal painting conditions. Do not use gas or diesel burners to heat the coated area as these produce water that will inhibit drying and curing. Poor ventilation may affect appearance and performance.

- Washability and final toughness will develop over several days as the paint hardens.

Maintenance

(after a minimum of four weeks' drying)

- When cleaning use a soft sponge with lukewarm water and a small amount of liquid detergent.

- See the Resene Caring for your paint finish brochure or the Resene website for full cleaning instructions.

Be PaintWise

For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your local Authority for disposal information.



CyberCote WB Flat
spray application
8035

Resene

the paint the professionals use



CyberCote WB Flat
spray application
1105

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Ph 1800 738 383 Visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045
Ph (04) 577 0500 Visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAJ, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Use on: Walls and ceilings (excludes wet areas).

Gloss level: Flat.

Coverage: 8.6 square metres per litre per coat.

The spreading rate recommended for this product will normally achieve hiding in one spray application. Some colours may require an additional coat to achieve hiding. Increased spreading rates can be used but additional coats may be needed to achieve required film build and hiding. See the Resene website for more information.

Dry time (minimum): 4 hours. Do not apply at temperatures below 10°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 6 hours. Dry and recoat times will vary with wet film applied and environmental conditions (extraction systems to achieve multiple room air changes will assist drying even under marginal environmental conditions).

Primer required: Yes, dependent on surface.

Usual number of coats: Two. Some colours may require an additional coat.

Application method: Airless spray/back roll.

Thinning: In hot conditions may be thinned with up to 5% Resene Hot Weather Additive to slow drying.

Clean up: Water.

Colour range: Selected Resene Total Colour System including B55252, Multi-finish, Whites & Neutrals and The Range.

Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. When using multiple packs of this product on the same project please mix them together before use. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.