



**Resene Paints (Australia) Limited  
Industrial & Marine Division**  
7 Production Avenue, Molendinar Qld 4214  
PO Box 924, Beenleigh Qld 4207  
Phone: 1800 738 383  
Fax: 1800 064 960  
ABN 65 050 034 529

## Summary of Slip Test Results

The following classifications are based on BPN results from test reports as indicated. They should not be used as a specification but as a starting point when designing a system for a particular situation. In each case appropriate primers and/or base coats will be required, please refer to technical support for full system specification.

Report No	Product	Aggregate and method	Classification	
			AS4586:2013	AS/NZS 4586:2004
AO2105151	<b>Carboguard 690</b>	Non Skid Fine – mixed at 50g/L	<b>P4</b>	W
BO300817-13	<b>Carboguard 2929</b>	Non Skid Medium – broadcast onto wet base coat	<b>P5</b>	V
BO300817-12	<b>Carboguard 2929</b>	Non Skid Fine - broadcast onto wet base coat	<b>P4</b>	W
BO300817-14	<b>Carbothane 133 LH</b>	Non Skid Medium - broadcast onto wet base coat	<b>P5</b>	V
BO300817-15	<b>Resene Uracryl 404</b>	Non Skid Medium - broadcast onto wet base coat	<b>P5</b>	V
BO300817-16	<b>Resene Uracryl 404</b>	SRG – mixed in at 500g/L	<b>P5</b>	V
BO300817-11	<b>Resene Non Skid Deck &amp; Path</b>	-	<b>P5</b>	V
BO300817-18	<b>Resene Walk-on</b>	SRG – mixed in at 500g/L	<b>P5</b>	V
BO300817-17	<b>Resene Walk-on</b>	-	<b>P4</b>	W
10-527919.77e	<b>Aquapoxy Semi Gloss</b>	SRG – mixed in at 500g/L	<b>P5</b>	V
10-527919.77d	<b>Aquapoxy Semi Gloss (top coated)*</b>	SRG – mixed in at 500g/L	<b>P3</b>	X
10-527919.77F	<b>Aquapoxy Gloss (NZ only) (top coated)*</b>	SRG – mixed in at 500g/L	<b>P3</b>	X

\*With these systems the layer containing slip resistant aggregate (SRG) was allow to cure and then top coated with gloss or semi-gloss as indicated. This enhances durability of the system at the expense of slip resistance.